



eco|right

# Design Guide

## The use of Hydraulic Lime Mortar



EcoRight Ltd  
Unit 2 Paddock Road  
Caversham, Reading  
Berkshire RG4 5BY  
Tel: 0845 873 3888

EcoRight Ltd, part of the Owlsworth Building Group, manufactures a comprehensive range of lime-based building products.

In a choice of natural earth tone colours for our hydraulic lime mortar range, we are able to achieve a solution for every lime building application.

The highest quality materials are used in our pre-blended products to ensure a consistency is achieved on the finished works.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works internationally to promote research and education and to encourage expertise and understanding in the use of building limes.

## Contents

1. Introduction
2. Background in the use of lime
3. Materials
4. Product data
5. Design considerations
6. Design Guide
7. Wall ties
8. Building with Lime
9. Summary

---

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      ® EcoRight is a registered trade mark



## Forward

Lime is one of the world's oldest building materials having been in use for centuries, dating back to the Egyptians, and many historical buildings are still in evidence today.

The use of lime mortar declined in the early part of the 20<sup>th</sup> Century, particularly after World War 2 and with the development of Portland cements. Revival of lime-based mortars requires the re-assessment in the construction of buildings or structures to take into account the characteristics and properties of modern factory blended lime mortars.

In the last 35 years, there has been a renaissance in the use of lime mortars as designers are now appreciating the benefits and applications in their design.

Lime mortars in the UK have stood the test of time from our Victorian heritage through to the modern commercial and residential buildings we see today.

## 1 INTRODUCTION

- 1.0 This guide has been prepared to assist Architects and Structural Engineers in utilising the benefits of EcoRight® natural hydraulic lime mortars.
- 1.1 Users of this guide will be experienced in the structural design of masonry to current British Standards & Building Regulations using cement-based mortars.
- 1.2 This document is for guidance only and the designer must satisfy themselves that this guide is applicable to their particular project/ application. It is the designers' responsibility for the overall design of the building.
- 1.4 This guide applies to all building types with masonry walls, loadbearing or non-loadbearing and also where lightweight steel framing forms the inner leaf. Given the number of permutations of masonry types, loading and wall geometry that are possible, it can only provide general guidance.
- 1.5 Specialist advice may need to be sought for unusual arrangements. Should any project not be covered by this generic guidance then please contact EcoRight Ltd to discuss the project further.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      ® EcoRight is a registered trade mark



## 2 BACKGROUND

- 2.1** Lime has been used as a traditional binder for centuries and generally we associate its use with historic building renovation or conservation.

There is now an increased interest in the use of natural hydraulic lime mortars in modern construction, enabling designers to appreciate the benefits of its use, not just for the repair of historic structures but also for new-build construction.

More research is now available, providing information on the properties and performance of lime mortar, so that standards can be set and design codes written with confidence. There is much published information available to assist the designer. ***'The use of lime-based mortars in new build' by the NHBC Foundation*** gives design data on mortar strengths for direct use in ***BS 5628, 'Code of practice for use of masonry'*** for the structural design of masonry. BS 5628-1 is now superseded but its replacement, BS EN 1996-1 does not include information for the use of lime mortars, so BS 5628-1 should continue to be used.

- 2.2** Paul Livesey, recognised as a leading industry expert, looks at the development in the use of lime as a building material in ***"Building limes in the United Kingdom"***. The book also examines its use today focusing on mix designs, aggregate types and durability.
- 2.3** For further details on the range of lime mortar products available from EcoRight Ltd, visit our website [www.ecoright.co.uk](http://www.ecoright.co.uk) or telephone 01189 469 150 or email [info@ecoright.co.uk](mailto:info@ecoright.co.uk).

## 3 MATERIALS

### 3.1 Identification

The dry mortar is available in 25kg bags, IBC's or silo options.

For large, individual projects and building developments, mortar can be supplied in silo form, which can hold up to 22 cubic metres or 35 tonnes of dry mix. The Silo is fitted with a control panel and "high-shear" mixer that regulates water input and mix flow, producing a consistent mortar at the touch of a button. For smaller projects the mortar is available in 25kg or bulk bags which can be then mixed in a conventional drum mixer.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      © EcoRight is a registered trade mark



EcoRight mortars are suitable for use in block laying and stone masonry work and also as a backing or final coat render/plaster.

EcoRight mortars are manufactured under factory conditions using natural hydraulic limes (NHL5 and NHL3.5) and a blend of well graded sharp sands.

All mortars are produced to EcoRight mix design recipes and marketed under the EcoRight brand - your assurance of quality and consistency

### 3.2 Authority

EcoRight mortars comply with the durability requirements of BS5628: Part 3:2005. Mortar strengths are measured at 91 days as opposed to 28 days, as lime mortars gain strength more gradually compared to Portland cement-based mortars. Now superseded by BS 1996 -1-1: 2005 Design of Masonry Structures. Also, BS EN 998-2: 2016 Specification for mortar for masonry.

Materials used conform to the following standards:

Sand	BS EN 13139: 2013 – Aggregates for mortar
Natural Hydraulic Lime (NHL)	BS EN 459: Part 1: 2015 – Building Limes
Calcium Lime (CL90)	BS EN 459: Part 1: 2015 – Building Limes
Pigments materials	BS EN 12878: 2014 – Pigments for the colouring of building materials
Admixtures	BS EN 934-1: 2008 – Admixtures for concrete, mortars and grouts

Water added on site should be clean and free from impurities.

### 3.3 General Advantages

EcoRight mortars offer several mix advantages:

- Consistent mix proportions
- Consistent quality of mortar
- Correct choice of sands
- Mortars can be re-worked for up to 24 hours
- Reduction in wastage
- Increased productivity as there is no need to allocate one individual for mixing.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      ® EcoRight is a registered trade mark



## 4. PRODUCT DATA

### 4.1 Manufacture

EcoRight mortars are manufactured using factory batching techniques.

Raw materials and end products are subject to regular quality control procedures and testing. The materials are weighed and mixed with rigorous quality control procedures.

Although mortar is traditionally specified by volume, it is generally accepted that batching by weight produces mortar of a greater consistency.

### 4.2 Mortar Mix Proportions

#### EcoRight Hydraulic Lime Mortar M5

With the following proportion 1:2. EcoRight M5 Hydraulic Lime Mortar will reach HLM5.0 (class III) at 28 days and HLM5 (class II) at 91 days (high resistance to freezing & thawing, high resistance to sulphates).

Mortar class	Lime : sand (vol/ vol)	BS 5628 Mortar mix Durability Designation	Hydraulic lime Mix designation	Typical Compressive strength (N/mm <sup>2</sup> @ 91 days)	Mortar Durability Class
M5	1: 2	(iv) at 28 days (iii) at 91 days	HLM5.0	5.0	7-8

#### EcoRight Hydraulic Lime Mortar M2.5

With the following proportion 1:2½. EcoRight M2.5 Hydraulic Lime Mortar will reach HLM1 (class IV) at 28 days and HLM2.5 (class III) at 91 days (good/high resistance to freezing & thawing, high resistance to sulphates).

Mortar class	Lime : sand (vol/ vol)	BS 5628 Mortar mix Durability Designation	Hydraulic lime Mix designation	Typical Compressive strength (N/mm <sup>2</sup> @ 91 days)	Mortar Durability Class
M2.5	1: 2½	(iv) at 28 days (iii) at 91 days	HLM2.5	2.5	5-6

The above is meant as a guide only; if you wish to discuss a specific application in further depth please call our sales office.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      © EcoRight is a registered trade mark



## 4.3 Performance

EcoRight mortars are more flexible than Portland cement-based mortars, allowing for increased movement joint spacing or avoiding movement joints altogether.

EcoRight mortars offer excellent vapour permeability, enabling buildings to “breathe”, preserving the brickwork.

EcoRight mortars are formulated to meet strength and durability requirements. Strength of lime mortars are normally specified at 91 days (see 5.3).

## 5 DESIGN CONSIDERATIONS

### 5.1 Considerations

Consideration on the use of lime mortar needs to be early in the design and planning stage and allow for the “constraints” of the material to be fully utilised as benefits, which are:

- More tolerance to movement
- Movement within the walls is accommodated in the bed joints therefore reducing the requirement for vertical joints
- Improved breathability – absence of condensation and dampness
- Capable of self-healing
- Less susceptible to sulphate attack
- Cold weather working
- Slow rate of strength gain
- Speed of construction

### 5.2 Mortar classification

Classification of mortar type to be used is dependent on exposure conditions and/ or loading (contact EcoRight Ltd for further guidance).

In general, a class M2.5 moderately hydraulic lime mortar will cover most applications for cavity wall construction, solid brick, blockwork and stonework.

If a higher level of durability is required such as parapets, chimneys or below dpc, then a class M5 hydraulic lime mortar should be used.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      © EcoRight is a registered trade mark



## 5.3 Mortar strength

Cement based mortars achieve their target strength and are tested at 28 days, however, for hydraulic lime mortars the strength development is much slower and design strength isn't achieved until 91 days.

Masonry constructed using a lime-based mortar will develop sufficient strength and resistance to vertical loading.

Consideration should be made if excessive lateral loadings are expected. Single skin brick or blockwork will have sufficient resistance to vertical loads.

## 6 DESIGN GUIDE

### 6.1 Design Benefits

The use of lime mortar allows any movement to be accommodated in the bed joints, therefore reducing the requirement for vertical movement joints. There is greater tolerance to movement, particularly in high buildings/structures (see 6.2).

Improved breathability allows moisture vapour to move freely through the mortar joint, reducing the likelihood of frost damage in the brickwork.

In the manufacturing process lime produces less carbon dioxide than cement as it is burnt at lower temperatures, saving on fuel consumption and emissions of pollution and greenhouse gases. CO<sup>2</sup> emissions are around 20% lower than in cement manufacture. Lime mortar will also absorb CO<sup>2</sup> during the hydration process (carbonation) and over a period of time become carbon neutral. Changing to a lime-based mortar will make a significant contribution in reducing CO<sup>2</sup> levels in the UK.

Due to lower bond strength, the bricks/masonry can be easily cleaned and recycled at the end of the building's life.

## 6.2 Movement Joints

EcoRight hydraulic lime mortars are designed to maximise the flexibility of the mortar without cracking. Combined with a very low coefficient of thermal expansion, enables masonry to be constructed without expansion or movement joints. The movement in a masonry wall can be accommodated in the bed joints.

Traditional masonry work did not use expansion joints, which actually made buildings much simpler and aesthetically more pleasing

**6.2.1** Lime mortars have an inherent flexibility to accommodate minor movements in brickwork, allowing movement joint spacing to be increased or avoided altogether. Movement is accommodated in the individual bed joints.

When movement occurs in a building, hairline cracks will form in the mortar joints, but due to the autogenous healing properties of lime mortar through carbonation, any micro cracks are sealed. This is the result of movement of rainwater through the surface and dissolving the free lime.

**6.2.2** In general, movement joint spacing can be increased by 2 ½ times the standard requirement for a cement-based mortar application, 30m for brickwork and 15m for blockwork. Reduced spacing will be necessary near to corners or in areas with many openings. In very large masonry panels without openings, it is possible to increase the spacing further, depending on the length to height aspect ratio.

**6.2.3** As significant movement can occur at the corners of buildings due to the brickwork sliding on the damp proof course (DPC), bed joint reinforcement can be installed to counteract the movement.

**6.2.4** Joint spacing needs to be considered on a project-by-project basis, giving due consideration to fully utilising the benefits of designing masonry using a lime mortar.

## 7 WALL TIES

The selection and spacing of wall ties are dependent on various factors. These include type of masonry, cavity width, height of structure and location. Refer to Eurocode 6 Design of Masonry Structures (BS EN 1996 -1-1 2005) for guidance.

### 7.1

Wall ties for use with lime mortars should be stainless steel and types 1, 2, 3 or 4 depending on design loading. Spacing is the same as for cement-based mortars. In large panels, differential movement can occur between the inner and outer leaf of a cavity wall construction. In this instance it is preferable and advisable to use flexible wall ties, to allow this movement and avoid cracking.

## 8 BUILDING WITH LIME

### 8.1 Rate of Laying

There is very little difference in the build rate between a cement based and lime-based mortar. Daily lift heights of 1.5m are possible. This applies for masonry units with an absorption of around 12-15%. For bricks with much lower absorption rates of 2-5% such as engineering bricks, there is a restriction on height generally as low as 2-3 courses per day. Consideration should be given on any temporary loading that may affect the build rate.

### 8.2 Pointing

Whenever possible, avoid recessed joints as they are likely to encourage water trapment in the bed joints and lead to potential joint failure. To allow rainwater to be shed the preferable option is flush pointing.

### 8.3 Winter Working

Working with lime mortar can proceed in winter providing adequate protection is given, as frost damage is very possible in the fresh mortar. In general, **mortar should not be used if the temperature is at 5°C and falling or 3°C and rising.** At below 5°C lime mortars will not harden until the temperature has increased above this level. It is therefore important to protect from the risk of frost attack.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      © EcoRight is a registered trade mark



## 8.3 Adverse weather conditions

Lime mortars do build up strength much slower and in extreme weather of direct sunlight, driving wind and rain, protection should be provided during the setting process.

## 8.4 Frost attack

Should frost damage occur in the freshly laid mortar then leave in place until weather conditions improve and simply rake out the joints and re-point. Under no circumstances should anti-freeze admixtures be used.

## 8.5 Sulphate attack

Due to the lower burning temperatures in the manufacture of hydraulic limes, there is an absence of Tri-calcium aluminate (C3A). As a result, lime mortars are less susceptible to sulphate attack

## 8.6 Weepholes

The breathability of lime mortars will allow any moisture that penetrates the façade to escape as water vapour through the joints.

The mortar will not allow driven rain to penetrate through the structure, with only the surface getting wet or saturated.

Therefore, water will not penetrate into the cavity. Any moisture will be drawn out through the mortar joints avoiding the need for weepholes.

EcoRight Ltd  
Unit 2 Paddock Road Industrial Estate  
Caversham  
Reading  
Berkshire  
RG4 5BY  
Tel: 01189 469 153  
Company Registration no: 6561874

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY  
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.  
© Copyright EcoRight Ltd 2018      ® EcoRight is a registered trade mark